

TEST REPORT

No. : GZIN2302000880ML01_EN

Date : 2023-03-10

Page: 1 of 2



CUSTOMER NAME: DONGGUAN GUANZHINIU JEWELRY CO.,LTD.
 ADDRESS: 402,4/F.YANGXIN SCIENCE PARK,NO.1,YONGSHENG ROAD,
 YONGTOU COMMUNITY,CHANG'AN TOWN,DONGGUAN CITY,ZIP
 CODE:523000

Sample Name : ASTM F136-13 TITANIUM LABRET
 Manufacturer : Dongguan Guanzhiniu Jewelry Co.,Ltd.

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : GZIN2302000473PL01, SHIN2303002774ML01
 Date of Receipt : 2023-02-28
 Testing Start Date : 2023-02-28
 Testing End Date : 2023-03-10
 Test result(s) : For further details, please refer to the following page(s)
 (Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
 SGS-CSTC Standards Technical
 Services Co., Ltd. Guangzhou
 Branch.

Shining Chan
 Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
 Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
 Guangzhou Branch, Inspection & Testing Laboratory

No.198, Kazhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
 中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155661 www.sgs.com.cn
 t (86-20) 82155661 sgs.china@sgs.com

TEST REPORT

No. : GZIN2302000880ML01_EN

Date : 2023-03-10

Page: 2 of 2

Chemical Composition Analysis

Element	Test Method	Req.(%)	Result (%)	Con.
C	ASTM E1941-10(2016)	≤0.08	0.007	Pass
O	ASTM E1409-13	≤0.13	0.11	Pass
N	ASTM E1409-13	≤0.05	0.003	Pass
Al	ASTM E2371-13	5.50~6.50	6.09	Pass
V	ASTM E2371-13	3.50~4.50	4.17	Pass
Fe	ASTM E2371-13	≤0.25	0.02	Pass
H*	GB/T 4698.15-2011	≤0.012	0.0071	Pass
Ti	ASTM E2371-13	Balance	Balance	Pass

Note: 1. The content test of H was carried out by external laboratory assessed as competent, the remaining elements were conducted by SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd. Laboratory.

2. The results comply with the requirement of ASTM F136-13



Sample Photo

Note: The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

*****End of report*****